



Silicones Simplified

www.xiameter.com

We help you
invent the future.™

dowcorning.com

DOW CORNING

Fluid Resistance Guide

Performance Profiles for *Silastic*® brand Silicone and Fluorosilicone Rubber and XIAMETER® brand Silicone Rubber

Contents

	Page
Introduction	2
Fluids Index	4
ASTM and IRM Oils, Fuels, and Fluids	6
MIL Specification Oils, Fuels, and Fluids	8
Automotive Oils and Fluids	11
Fuels	14
Hydraulic Fluids	15
Transformer and Instrument Oils	17
Specialty Oils, Greases, and Fluids	18
Solvents	21
Silicone Fluids	23
Silicone Compounds and Greases	25
Food Products	26
Water and Steam	28
Acids	29
Bases	30
Salts	31
Other Chemicals	31

Introduction

This guide is intended to give you an idea of the performance profile of various classes of silicone rubbers when immersed in different fluids. It's our hope that the information will save you the time and cost of preliminary screening and feasibility tests. We recommend that you test specific materials prior to use. Keep in mind that service conditions are usually less severe than immersion tests. For instance, in actual service the rubber is often only partly exposed or is subjected only to spills or splashing. This means that a rubber that shows only fair results in a prolonged total immersion test will often perform quite adequately under actual conditions.

Types of Silastic and XIAMETER Silicone Rubbers

Immersion test results refer to types of silicone rubber by their ASTM designation. The polymer classification described in ASTM D 1418 is based on the organic group side chains attached to the silicon-oxygen chain. If other groups are present, their initials are listed prior to the MQ designation: MQ indicates methyl groups, V indicates phenyl groups. Where several types of rubber have been tested for resistance to one fluid, they are listed in this order in the tables:

Silastic and XIAMETER Silicone Rubbers

MQ } General purpose stocks
VMQ }

PMQ } Extremely low-temperature stocks
PVMQ }

Silastic Fluorosilicone Rubbers

FVMQ Fuel-, oil-and solvent-resistant stocks

Effects of Immersion

If a fluid affects a silicone rubber at all, after prolonged immersion and usually at elevated temperatures, the changes are evidenced as increases or decreases of several physical properties: hardness, tensile strength, elongation, and volume. The values that appear in the tables have been calculated as prescribed in ASTM D 471. The figures have been rounded and represent typical values.

The effects that have been tabulated often go hand in hand, but there is no quantitative correlation. For example, a silicone rubber in one fluid may swell 10 percent and lose 15 percent in tensile strength, whereas in another fluid the same rubber may also swell 10 percent but lose 30 percent in tensile strength.

The effects of solvent or fuel immersion often proceed until they reach a limit and then increase no more. This limit corresponds to the maximum amount of solvent or fuel that the rubber structure can absorb at the test temperature. While a fluid may produce little effect at room temperature, it may cause a noticeable change at 204°C (400°F).

Swelling caused by fluid penetration of rubber is usually the most obvious effect. However, this swelling does not necessarily indicate permanent deterioration. The rubber often regains most of its original properties after the fluid has evaporated.

Hardness changes are tabulated in durometer points on the Shore A-2 scale. Changes in tensile strength and elongation are expressed as percentages of the original values. These changes are usually losses that appear as negative values. Volume changes due to penetration of fluids between silicone polymer chains appear as positive values, that is, swelling. Negative volume changes indicate chemical degradation, such as the tables show for 20 percent sulfuric acid at 83°C (180°F) for seven days.

Service Considerations

Duration of exposure may be very important in some applications. In the case of silicone rubber used as electrical insulation, this may mean that no permanent harm will result from short exposures to washing or rinsing, even with powerful solvents. After prolonged periods at high temperatures, hydrocarbon oils may slowly decompose. The breakdown products may have an entirely different solvent effect than that of the original oil. On the other hand, heating may sometimes have the favorable result of driving off volatile components of oils.

Contamination in service may also produce changes in lubricating oils and their effect as immersion media. Swelling may be a limiting factor in service, even though a small amount may be desirable for certain applications. For example, o-rings often work better if they swell slightly in the fluid they seal; but if they swell too much, they may push themselves out of position and lose effectiveness. Also, swelling may produce tears in tightly restricted parts.

Selection Recommendations

1. *Silastic®* brand fluorosilicone rubber shows superior resistance to many fluids; however, other types of rubber offer better resistance to acetone, certain other ketones, and some esters. The fluorosilicone polymer can be blended with other silicone polymers to obtain resistance intermediate between the two types.
2. The higher the aromatic or phenyl content of oils and fuels, the greater is their effect on most types of silicone rubber except fluorosilicone rubber. The stocks most affected are usually the types with ASTM designations including P (phenyl groups). This follows the common principle of organic to solvents that "like dissolves like."
3. For high-temperature applications, parts should generally be cured at temperatures higher than anticipated service temperatures, no matter whether the parts will contact liquid or air. Property changes are usually less for fully cured parts than for as-vulcanized or partially cured parts.

Test Conditions

The immersion tests tabulated were conducted according to ASTM D 471. Specimens were cut from slabs that were molded and oven-cured in accordance with recommended procedures for the individual stocks.

Many fluids were tested only for their effects on volume and hardness because these values are usually the most critical.

In regard to the limited correlation between test conditions and service conditions, the most widely used test, ASTM D 471, states:

"Owing to the wide variations often present in service conditions, no direct correlation between this accelerated test and service performance may be given or implied. However, the method yields comparative data on which to base judgment (as to service quality and is especially useful in research and development work)."

Test results refer to types of silicone rubber products by ASTM designation. Because tests were conducted over a period of several years, the specific products used may no longer be available. Test results, therefore, can be used to project general performance only. If more specific information is required, refer to individual data sheets or conduct new tests.

Fluids Index

Classification of Immersion Media

Fluids for testing have often been submitted with only a trade name for identification. It has been difficult to classify some of these fluids for the tabular sections of this guide. The overall classification has been designed for easy reference by users in different industries.

A	Coca-Cola Syrup	26	G		
Acetic Acid	29	Coffee	26	Gas Drip Oil	19
Acetone	21	Coolanol 35	18	Gasohol	15
Acetonitrile	31	Coolanol 45	18	Gasoline	14
Aroclor 1254	19	Copper Sulfate	31	GE Transil Oil	19
Aerosafe 2300	15	Cosmoline 2046	19	GM Hydraniatic Fluid (Type A)	12
Ammonia	31	Crude Oil 7 API	19	GM 14X Heavy Duty Oil	19
Ammonium Hydroxide	30	Crude Oil 315 API	19	Gulf Synthetic Lube No. 2 Oil	10
AMOCO Super Permable 10W-30	11	Cyclohexane	22		
ANG 15 Industrial Grease	18			H	
ANG 25 Diester Base	18			Heptane	22
ANG 25 Glycerol Ester	18	D		HMS 20-1083	33
Aniline	31	Delco No. 9	19	Hydrazine	33
ANO No. 3 Grade M; Extreme Pressure	18	Delco No. 11	19	Hydrochloric Acid	29
ANO No. 6 Oil	18	Delco Shock Absorber Fluid	13	Hydrofluoric Acid	29
ANO No. 9 Oil	18	Delco Supreme 550		Hydrogen Peroxide	33
ANO No. 11 Oil	18	Heavy-Duty Brake Fluid	13	Hydrolube H-2 Fluid	15
ANO No. 366 Oil	18	Diacetone Alcohol	22	Hypoid EP Lubricant	13
Aroclor 1254	19	Dichloroisopropyl Ether	22		
Askerol Transformer Oil	17	Diesel Fuel	14		
ASTM No. 1 Oil	6	Diethyl Ether	22	I	
ASTM No. 2 Oil	6	Di (2-Ethylhexyl) Sebacate	7	Inerteen Transformer Oil	17
ASTM No. 3 Oil	6	Dimethyl Formamide	32	IRM 902 Oil	7
ASTM reference fuel A Isoctane	7	Diocetyl Phthalate	32	IRM 903 Oil	7
ASTM Reference Fuel B	8	Dowtherm A Heat Transfer Oil	19	Isooctane	7
ASTM Reference Fuel C	8	Dowtherm 209	32	Isopropyl Alcohol	22
ASTM Test Fluid 101	7	Dow Corning® brand Compounds	25, 26	Isopropyl Nitrate	33
		Dow Corning® brand Fluids	24, 25		
		Dow Corning® brand Greases	25, 26	J	
		Dynaflow Automatic Transmission Fluid	12	JP-4 Fuel	14
B				JP-5 Fuel	14
Beer	26	E		JP-8 Fuel	14
Benzene	21	Ethanol	15		
Brayco 880D Oil	10	Ethyl Alcohol	22	L	
Bromine (liquid)	31	Ethylenedichloride	22	Lard	26
Butter (liquid)	26	Ethylene Glycol	32	Lithium Hydroxide	30
Butyl Acetate	22	Ethylene Oxide	32		
Butyl Alcohol	22	Exxon Turbo Oil No. 15	9	M	
Butylene Oxide	31	Exxon Univis J-43 Oil	9	Manufactured Gas	14
		Exxon WS2406 Fluid	15	Mazola Oil	26
C				Methanol	8, 15
Calcium Oxide	30	F		Methyl Alcohol	22
Calcium Silicate	31	FC-75 Fluorochemical Fluid	19	Methyl Chloride	22
Caprolactam Monomer	31	Ferric Chloride	31	Methylene Chloride	22
Carbon Tetrachloride	22	Freon	32, 33	Methyl Methacrylate	33
Chlorobromomethane	22			MIL-A-8243 Deicer Fluid	10
1-Chlorodecane	32			MIL-H-5606	9
Chloroform	22			MIL-H-5606 Oil	9
Chlorothene Solvent	22			MIL-J-5624F-14	14

MIL-L4600 Oil Bis	11	PQ 4226	9	Tetrahydrofuran	34
MIL-L-7808D Oil	9	PQ 8365	10	Texaco 10W 30 Motor Oil	11
MIL-L-7808E Oil	10	PRL 3313	20	Texaco Regal Starfak	
MIL-L-7808E, F, and G Oil	10	Propylenedichloride	23	Special Grease	18
MIL-L-7808F Oil	10	Propylene Oxide	34	Texaco TG-749	18
MIL-L-7808G Oil	10	Pydraul Fluids	16	Texamatic A Transmission Fluid	12
MIL-7808J Jet Engine Oil	11	Pyranol Transformer Oil	17	Texamatic C Transmission Fluid	12
MIL-L-23699 Oil	10			Texamatic TL 3528	
MIL-O-6085 Oil	9	R		Transmission Fluid	12
Mineral Oil	19	RCA-Gulf Instrument Oil A	17	Texas 1500 Oil (HD Concentrate)	20
Mineral Oil (Shell No. 5)	19	Royco 808GF Oil	10	Tia Maria Liquor	27
Mineral Spirits	22	RX-1099 (Vinyl Plastisol)	34	TL 3450 Lubricant	13
Mobil 5W-30HP Engine oil	11			Toluene	23
Mobil Jet II Oil	11	S		Toluene Vapor	23
Mobil Oil No. 20 Oil	11	SAE No. 10 Oil	11	TTs-735 Type VII	9
Mobilube GX-90 General Lubricant	13	SAE No. 20 Oil	11	Trichloroethylene	34
Mobil XRM-139A Oil	10	Salicylanilide	34	Tricresyl Phosphate	21
Molybdenum Disulfide	33	Santicizer 141	34	Trifluorochloroethylene	34
Monochlorobenzene	22	Scotch Whisky	27	Turbo Oil No. 35	21
Monoethanolamine	33	SG 4766 Glycol Ester Base Grease	20	Turpentine	23
Motor Oil - 10W-30	11	Shell Aircraft Turbine Lubricants	20		
		Shell B & B Grease	20	U	
		Skydrol Fluids	16, 17	Ucon Lubricants	21
Naphtha	23	Socony Mobil RL 147-A No. 7	20	Univolt 35 Transformer Oil	17
Navy Crankcase Oil No. 2135	20	Socony Mobil Transmission Fluid		Unsymmetrical Dimethyl	
Navy Crankcase Oil No. 9250	20	(Type A)	12	Hydrazine	15
N-43 Fluorocarbon Capacitor Fluid	17	Sodium Carbonate	31		
Nitric Acid	29, 30	Sodium Chloride	31	V	
Nitrocellulose Solvent	23	Sodium Hydroxide	31	Vegetable Oil	27
No Lead Gasolines	15	Solvatone Solvent	23	Vinegar	27
		Spry Shortening	27		
		Standard Oil Shock		W	
1-Chlorodecane	32	Absorber Fluid	13	Wagner 21B Brake Fluid	13
Oil	26, 27	Staufferjet II Oil	10	Water	28
Orange Peel Oil	26	Steam	28, 29	Wemco C Transformer Oil	18
Orange Syrup	27	Stoddard Solvent	23	White Gasoline Vapors	14
Oronite Fluids	15, 16	Styrene Monomer	34		
Ortho-Chloroethylbenzene	23	Sulfur	34	X	
Ortho-Chlorotoluene	23	Sulfur Dioxide	34	XIAMETER® PMX-200 Silicone Fluid	23, 24
Oxylene Solvent	23	Sullur Hexafluoride	34	Xylene	23
		Sulfuric Acid	30		
		Sun Oil No. 8 X2513-I L	20		
Pacemaker Fluid 100T	20	Sun 5W-3 Auto Engine Oil	11		
Pentachlorophenol	33	Sun 109 Transmission Fluid	12		
Perchloroethylene	23	SUNOCO HD	11		
Phenol	33	Swan Finch EP90 Lubricant	13		
Phosphoric Acid	30				
Phthalic Acid Anhydride	33	T			
Phthalic Anhydride	33	Tab Concentrate	27		
Polyglycol	34	Tar	34		
Polystyrene	34	Tectyl 502C Rust Inhibitor	20		
Potassium Hydroxide	30	Tectyl 511-M Rust Inhibitor	20		

ASTM and IRM Oils, Fuels and Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ASTM No. 1 Oil	VMQ PVMQ	3 days/25°C (77°F)	nil -5	- -	- -	nil 5
	MQ VMQ PVMQ	3 days/100°C (212°F)	-5 -5 -10	-5 -10 -10	-5 -5 -10	5 5 10
	MQ VMQ PVMQ	1 day/150°C (302°F)	-10 -5 -10	-10 -10 -15	5 -10 -10	5 10 10
	MQ VMQ PVMQ FVMQ	3 days/150°C (302°F)	-10 -10 -10 -5	-10 -5 -20 nil	nil -5 -15 -5	5 10 10 nil
	MQ VMQ PVMQ	7 days/150°C (302°F)	-10 -10 -10	-10 -10 -20	-10 -10 -10	10 10 10
	VMQ	30 days/150°C (302°F)	-10	-35	-25	10
	MQ VMQ PVMQ	3 days/177°C (350°F)	-10 -5 -15	-10 -10 -20	-10 -10 -10	5 10 10
	VMQ	7 days/177°C (350°F) 14 days/177°C (350°F)	-20 -20	-50 -50	-30 -30	10 10
	VMQ FVMQ	70 hr/150°C(302°F)	-6 nil	4 nil	-2 -14	1 1
ASTM No. 2 Oil	VMQ FVMQ	7 days/150°C (302°F)	-6 -2	8 1	nil -13	8 1
	MQ PVMQ	3 days/24°C (75°F)	-5 -10	- -	- -	15 25
ASTM No. 3 Oil	MQ PVMQ	3 days/100°C (212°F)	-10 -15	- -	- -	20 35
	PVMQ FVMQ	7 days/110°C(230°F)	-30 -5	-75 -5	-60 -5	60 5
	MQ VMQ PVMQ FVMQ	1 day/150°C (302°F)	-20 -15 -25 -5	-50 -35 -40 -10	-20 -20 -20 10	50 45 50 5
	MQ VMQ PVMQ PVMQ FVMQ	3 days/150°C (302°F)	-25 -20 -35 -25 -5	-50 -45 -50 - -25	-25 -25 -30 - -10	35 35 55 85 5
	VMQ FVMQ	7 days/150°C (302°F)	-25 -5	-45 -17	nil -15	40 5
	FVMQ	14 days/150°C (302°F) 21 days/150°C (302°F) 28 days/150°C (302°F)	-5 -10 -10	-25 -60 -85	5 5 -20	5 5 5

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

ASTM and IRM Oils, Fuels and Fluids (cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ASTM No. 3 Oil (cont.)	VMQ	4 hr/177°C (350°F)	-25	-35	-25	45
	MQ VMQ PVMQ FVMQ	3 days/177°C (350°F)	-35 -40 -40 -10	-85 -60 -65 -25	-25 -15 5 5	55 60 70 5
	VMQ FVMQ	7 days/177°C (350°F)	-50 -10	-80 -40	-30 5	70 5
	VMQ	3 days/200°C (392°F)	-15	-45	nil	5
	FVMQ	14 days/200°C (392°F)	-25	-40	-10	nil
IRM-902 Oil	VMQ PVMQ FVMQ	3 days/23°C (73°F)	-5 -8 -6	-12 -12 -7	-14 -12 -1	5 7 1
	VMQ PVMQ FVMQ	3 days at 150°C (302°F)	-6 -16 0	-7 -7 -7	-17 -21 -8	10 19 1
	VMQ PVMQ FVMQ	3 days/23°C (73°F)	-12 -21 -4	-7 -31 -7	-11 -23 -3	18 33 1
IRM-903 Oil	VMQ PVMQ FVMQ	3 days/150°C (302°F)	-26 -33 -2	-23 -68 -11	-28 -62 -15	40 84 2
	FVMQ (70 Durometer)	70 hours/150°C (302°F) 7 days/150°C (302°F)	-4 -3	-8 -9	4 6	2 2
	FVMQ	7 days/135°C (275°F) 48 hr/150°C (302°F) 7 days/100°C (212°F)	-4 -10 -15 -10	-7 -25 -	-11 -25 -	5 10 20 20
ASTM Test Fluid 101 Di (2-Ethylhexyl) Sebacate +0.5% Phenothiazine Di (2-Ethylhexyl) Sebacate (Plexol-201)	FVMQ	4 days/232°C (450°F)	DT	DT	DT	DT
ASTM Reference Fuel A - Isooctane (also TTS-735 Type I)	VMQ PMQ PVMQ	5 min/-54°C (-65°F)	-	-	-	10
	VMQ PMQ PVMQ	10 min/-54°C (-65°F)	-	-	-	10
	VMQ PMQ PVMQ	30 min/-54°C (-65°F)	-	-	-	10
	VMQ PMQ PVMQ	5 min/24°C (75°F)	-	-	-	20
	VMQ PMQ PVMQ	10 min/24°C (75°F)	-	-	-	20
	VMQ PMQ PVMQ	30 min/24°C (75°F)	-	-	-	15
	VMQ PMQ PVMQ	7 days/24°C (75°F) 3 days/150°C (302°F)	-5 -20	-40 -60	-30 -30	30
	FVMQ	7 days/24°C (75°F)	DT	DT	DT	30

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

ASTM and IRM Oils, Fuels and Fluids (cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ASTM Reference Fuel B (70% Isooctane, 30% Toluene by Volume) (also TTS-735 Type III)	FVMQ	1 day/-54°C (-65°F) 3 days/24°C (75°F) 7 days/24°C (75°F) 14 days/24°C (75°F)	-5 -5 -5 -10	-20 -55 -40 nil	-20 -35 -30 -30	10 20 20 15
	VMQ FVMQ	3 days/65°C (150°F)	-5	-50	-40	215 15
	FVMQ	3 days/150°C (302°F) 3 days/232°C (450°F)	-20 DT	-60 DT	-35 DT	30 DT

MIL Specification Oils, Fuels and Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ASTM Reference Fuel C (M0)	FVMQ (60 Durometer)	1 day/23°C (73°F) 1 week/23°C (73°F) 3 months/23°C (73°F) 1 year/23°C (73°F) 1 day/60°C (140°F) 1 week/60°C (140°F) 3 months/60°C (140°F) 6 months/60°C (140°F)	-15 -14 -14 -13 -14 -14 -17 -14	-25 -20 -23 -22 -30 -36 -37 -33	-23 -19 -20 -18 -15 -32 -28 -35	18 19 19 19 21 21 22 21
85% ASTM Reference Fuel C 15% Methanol (M15)	FVMQ (60 Durometer)	1 day/23°C (73°F) 1 week/23°C (73°F) 3 months/23°C (73°F) 1 year/23°C (73°F) 1 day/60°C (140°F) 1 week/60°C (140°F) 3 months/60°C (140°F)	-24 -18 -18 -14 -21 -21 -24	-52 -56 -50 -53 -57 -64 -64	-29 -42 -38 -38 -41 -48 -45	26 24 25 24 29 31 31
75% ASTM Reference Fuel C 25% Methanol (M25)	FVMQ (60 Durometer)	1 day/23°C (73°F) 1 week/23°C (73°F) 3 months/23°C (73°F) 1 year/23°C (73°F) 1 day/60°C (140°F) 1 week/60°C (140°F) 3 months/60°C (140°F) 6 months/60°C (140°F)	-19 -19 -18 -13 -20 -23 -26 -27	-53 -54 -50 -51 -63 -62 -68 -64	-43 -40 -39 -36 -51 -48 -48 -45	26 25 25 24 32 33 33 28
50% ASTM Reference Fuel C 50% Methanol (M50)	FVMQ (60 Durometer)	1 day/23°C (73°F) 1 week/23°C (73°F) 3 months/23°C (73°F) 1 year/23°C (73°F) 1 day/60°C (140°F) 1 week/60°C (140°F) 3 months/60°C (140°F)	-18 -18 -19 -17 -21 -22 -24	-52 -48 -49 -50 -60 -59 -64	-41 -37 -39 -33 -47 -46 -43	25 24 23 22 29 30 28
15% ASTM Reference Fuel C 85% Methanol (M85)	FVMQ (60 Durometer)	1 day/23°C (73°F) 1 week/23°C (73°F) 3 months/23°C (73°F) 1 year/23°C (73°F) 1 day/60°C (140°F) 1 week/60°C (140°F) 3 months/60°C (140°F)	-15 -14 -11 -11 -17 -18 -15	-36 -37 -32 -38 -38 -42 -50	-27 -19 -21 -20 -24 -20 -31	14 13 11 11 15 14 8
60% ASTM Reference Fuel C 40% Methanol by Volume (M40)	FVMQ (75 Durometer)	24 hours/110°C (230°F)	-30	-66	-50	46

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

MIL Specification Oils, Fuels and Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
TTS-735 Type VII (30% Toluene, 10% Isooctane, 59% Cyclohexane, 1.0% n-Butyl Disulfide)	FVMQ	3 days/24°C (75°F) 3 days/100°C (212°F)	-10 -10	-40 -40	-25 -35	20 20
MIL-H-5606 Oil (Exxon Univis J-43)	VMQ PVMQ	14 days/24°C (75°F)	- -	- -	- -	65 95
	MQ PMQ FVMQ	1 day/71°C (160°F)	-20 -30 -5	-75 -65 -30	-60 -55 -10	160 120 5
	FVMQ	3 days/71°C (160°F)	-10	-30	-15	5
	VMQ PVMQ	14 days/71°C (160°F)	- -	- -	- -	80 110
	FVMQ	19 days/121°C (250°F) 3 days/150°C (302°F) 3 days/177°C (350°F) 7 days/177°C (350°F) 3 days/200°C (392°F)	-10 -10 -20 -20 -35	-10 -35 -50 -55 -85	-15 -10 -10 5 15	5 10 10 10 15
MIL-H-5606 (American Oil PQ 4226)	FVMQ	70 hr/150°C (302°F)	-6	-8	-16	6
MIL-O-6085 Oil	FVMQ	14 days/177°C (350°F)	-20	-70	-15	10
MIL-L-7808D Oil (Exxon Turbo Oil No. 15)	FVMQ	1 day/-54°C (-65°F)	-5	-15	nil	nil
	MQ VMQ PMQ	3 days/24°C (75°F)	-5 -10 -10	-10 -10 -25	nil -5 -15	10 10 20
	PVMQ	3 days/24°C (75°F) 7 days/24°C (75°F)	-15 -25	-10 -55	-5 -40	20 30
	VMQ PMQ	3 days/71°C (160°F)	-15 -15	-10 -45	-10 -40	15 30
	MQ VMQ PMQ PVMQ	7 days/71°C (160°F)	-10 -10 -20 -25	- - - -65	- - - -50	15 15 30 35
	MQ VMQ PMQ	1 day/121°C (250°F)	-10 -10 -10	- - -	- - -	20 20 40
	VMQ FVMQ	3 days/121°C (250°F)	-10 -5	-25 nil	-20 nil	20 5

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

MIL Specification Oils, Fuels and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
MIL-L-7808D Oil (Exxon Turbo Oil No. 15)	MQ VMQ PMQ	1 day/150°C (302°F)	-10 -5 -10	- - -	- - -	15 10 20
	VMQ PVMQ FVMQ	3 days/150°C(302°F)	-15 -25 -5	-40 -45 -15	-10 5 nil	25 40 10
	MQ	1 hr/177°C (350°F)	-10	-	-	10
	FVMQ	1 day/177°C (350°F)	-10	-35	-10	10
	MQ VMQ PMQ PVMQ FVMQ	3 days/177°C (350°F)	-30 -35 -25 -35 -15	-65 - -50 -55 -40	-5 - -15 -15 -10	35 30 45 50 5
	FVMQ	7 days/177°C (350°F) 14 days/177°C (350°F) 1 day/200°C (392°F)	-20 DT -30	-60 DT -70	nil DT -15	10 DT 15
	VMQ FVMQ	3 days/200°C (392°F)	-35 -45	- -95	- -45	30 15
MIL-L-7808E Oil (Brayco 880D)	VMQ FVMQ	70 hr/150°C (302°F)	-20 -5	-35 -80	-10 -60	25 5
	VMQ FVMQ	70 hr/177°C (350°F)	-35 -5	-75 -95	-30 -90	25 -5
MIL-L-7808E, F, and G Oil (StaufferJet I)	VMQ FVMQ	70 hr/150°C (302°F)	-20 -10	-25 -25	-10 -25	25 10
	VMQ FVMQ	70 hr/177°C (350°F)	-35 -15	-65 -60	-10 -35	35 10
MIL-L-7808F Oil (Gulf Synthetic Lube No. 2)	FVMQ	70 hr/150°C (302°F)	-10	-30	-15	15
MIL-L-7808F Oil (Royco 808GF)	FVMQ	70 hr/150°C (302°F) 70 hr/177°C (350°F)	-10 -20	-45 -60	-15 -20	10 15
MIL-L-7808F Oil (Brayco 880G)	FVMQ	70 hr/150°C (302°F)	-15	-30	-20	10
MIL-L-7808G (Amendment 2) PQ8365	VMQ FVMQ	70 hr/150°C (302°F)	-14 -8	-21 -9	-19 -24	25 8
MIL-A-8243 Deicer Fluid	PVMQ	70 hr/71°C (160°F)	-5	-15	-10	nil
MIL-L-23699 Oil (Mobil XRM-139A)	FVMQ	96 hr/177°C (350°F)	-15	-	-	10
StaufferJet II Oil	FVMQ	70 hr/177°C (350°F)	-8	-25	-21	12
	VMQ FVMQ	100 hr/177°C (350°F)	-9 -9	2 -19	42 -36	11 12
	VMQ FVMQ	300 hr/177°C (350°F)	-8 -15	-3 -73	50 -33	7 9

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

ASTM and MIL Specification Oils, Fuels and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Mobil Jet II Oil	VMQ FVMQ	22 hr/25°C (77°F)	- -	- -	- -	4 3
	VMQ FVMQ	70 hr/150°C (302°F)	-10 nil	10 20	15 -35	10 10
	VMQ FVMQ	7 days/1500C(302°F)	-10 nil	10 5	25 -35	10 10
MIL-L-4600 Oil Bis (2-Ethylhexyl) Sebacate	PVMQ	3 days/25°C (77°F) 7 days/25°C (77°F)	-14 -14	- -	- -	28 30
MIL-L-7808J Jet Engine Oil	75% FVMQ 25% VMQ Blend.	22 hours/24°C (75°F)	-6	-28	-22	4

Automotive Oils and Fluids

Motor Oils

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
SAE No. 10 Oil (Sunoco HD)	FVMQ	3 days/150°C (302°F)	-5	-5	nil	nil
	MQ PMQ	1 day/100°C (212°F)	- -	- -	- -	10 20
	MQ PMQ	1 day/121°C (250°F)	- -	- -	- -	15 25
	MQ PMQ	1 day/150°C (302°F)	- -	- -	- -	15 25
10W-30 Motor Oil (Texaco)	FVMQ	15 days/177°C(350°F) 30 days/177°C (350°F)	-4 1	-33 -52	-8 -58	2 1
	50/50 VMQ/FVMQ	15 days/177°C (350°F) 30 days/177°C (350°F)	-16 -9	-35 -76	10 -80	9 3
AMOCO Super Permalube 10W-30	VMQ	250 hr/150°C (302°F)	-18	-21	5	23
Sun 5W-30 SJ Auto Engine Oil	FVMQ (70 Durometer)	70 hours/150°C (302°F) 7 days/150°C (302°F)	-1 1	1 -3	0 -6	0 0
Mobil 5W-30 HP Engine Oil	75% FVMQ 25% VMQ Blend.	3 days/150°C (302°F) 7 days/150°C (302°F)	-9 -9	-21 -26	-15 -22	12 12

MQ - methyl groups only

V - vinyl groups

P - phenyl groups

F - fluorine-containing groups

Automotive Oils and Fluids (Cont.)

Automobile Transmission Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Dynaflow Automatic Transmission Fluid	MQ VMQ PMQ	70 hr/93°C (200°F)	-15 -15 -10	- - -	- - -	15 25 35
GM Hydramatic Fluid (Type A)	VMQ FVMQ	3 days/150°C (302°F)	-35 -5	-40 -10	-5 -5	35 5
Socony Mobil Transmission Fluid (Type A)	MQ PMQ	1 day/121°C (250°F)	-10 -10	- -	- -	35 40
	MQ	7 days/121°C(250°F)	-10	-	-	35
Sun 109 Transmission Fluid	VMQ	100 hr/177°C (350°F)	-25	-40	nil	30
Texamatic A Transmission Fluid (Texaco)	VMQ	70 hr/65°C (150°F)	-10	-	-	10
	VMQ PVMQ FVMQ	70 hr/150°C (302°F)	-20 -30 nil	-30 -85 -25	-10 -65 -15	25 65 nil
	VMQ	70 hr/177°C (350°F)	DT	DT	DT	DT
Texamatic C Transmission Fluid (Texaco)	MQ PMQ	1 day/121°C (250°F)	-10 -10	- -	- -	35 45
	MQ VMQ	7 days/121°C (250°F) 70 hr/150°C (302°F)	-20 -25	- -60	- -25	40 25
Texamatic TL 3528 Transmission Fluid (Texaco)	VMQ	70 hr/121°C (250°F)	-15	5	nil	25

MQ - methyl groups only

V - vinyl groups

P - phenyl groups

F - fluorine-containing groups

DT - deteriorated

Automotive Oils and Fluids (Cont.)

Transmission and Differential Lubricants

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Hypoid EP Lubricant	FVMQ	14 days/149°C (300°F)	-20	nil	-10	nil
Mobilube GX-90 General Lubricant	VMQ FVMQ	3 days/149°C(300°F)	DT DT	DT DT	DT DT	DT DT
Swan Finch EP90 Lubricant	FVMQ	3 days/121°C (250°F) 3 days/150°C (302°F)	-10 DT	-70 DT	nil DT	-10 DT
TL 3450 Lubricant	VMQ	3 days/100°C (212°F)	-10	-	-	15
	VMQ FVMQ	3 days/121°C (250°F)	-10 -5	-60 -5	-45 -5	10 5
	VMQ FVMQ	3 days/150°C (302°F)	DT DT	DT DT	DT DT	DT DT

Shock Absorber Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Delco Shock Absorber Fluid	PMQ	3 days/71°C (160°F)	-	-	-	65
Standard Oil Shock Absorber Fluid	MQ VMQ	1 hr/150°C (302°F)	-15 -20	-	-	25
	MQ VMQ	1 hr/177°C (350°F)	-15 -20	-	-	30 45

Brake Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Wagner 21B Brake Fluid	MQ VMQ PVMQ	7 days/24°C (75°F)	-5 0 -5	-	-	5
	PVMQ FVMQ	3 days/150°C (302°F)	-5 DT	-90 DT	-85 DT	10 DT
	MQ VMQ PVMQ	7 days/88°C(190°F)	-5 -5 -5	-	-	5 5 5
Delco Supreme 550 Heavy-Duty Brake Fluid	VMQ	70 hr/150°C (302°F)	-4	-25	nil	4

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Fuels

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Diesel Fuel	MQ VMQ PVMQ	7 days/24°C (75°F)	-25 -25 -35	- - -	- - -	85 100 130
	MQ VMQ PVMQ	7 days/54°C (130°F)	-25 -30 -40	- - -	- - -	90 105 140
Gasoline	VMQ PVMQ	5 min/24°C (75°F)	- -	- -	- -	25 20
	VMQ PVMQ	30 min/24°C (75°F)	- -	- -	- -	60 75
	MQ	18 hr/24°C (75°F)	-25	-	-	245
Gasoline -Regular	FVMQ	24 hr/25°C (77°F)	-12	-39	-30	21
Gasoline -Low Lead	FVMQ	24 hr/25°C (77°F)	-12	-41	-30	20
White Gasoline Vapors	PMQ	14 days/24°C (75°F)	-10	-	-	50
	VMQ	7 days/24°C (75°F)	-20	-	-	165
JP-4 Fuel (MIL-J-5624F)	FVMQ	1 day/-54°C (-65°F)	-5	-10	nil	nil
	PVMQ	10 min/24°C (75°F)	-10	-	-	30
	PVMQ FVMQ	1 day/24°C (75°F)	-5	-20	-50	105 10
	FVMQ	3 days/24°C (75°F)	-5	-35	-20	10
	PVMQ FVMQ	7 days/24°C (75°F)	-25 -5	-75 -20	-60 -50	330 10
	FVMQ	14 days/24°C (75°F) 21 days/24°C (75°F) 30 days/24°C (75°F) 3 days/115°C (240°F) 15 days/121°C (250°F) 3 days/177°C (350°F) 3 days/200°C (392°F) 3 days/232°C (450°F)	-5 -5 -5 -5 -20 -25 -35 -45	-20 -30 -30 -55 -65 -65 -80 -90	-50 -55 -55 -40 -40 -20 -10 -20	10 10 10 15 20 25 30 20
	FVMQ	7 days/24°C (75°F)	-5	-15	nil	5
JP-5 Fuel (MIL-J-5624F)	FVMQ	7 days/24°C (75°F)	-5	-15	nil	5
JP-5 Fuel Jet Engine Oil	75% FVMQ 25% VMQ Blend.	22 hours/24°C (75°F)	-11	-45	-37	21
JP-8 Fuel	FVMQ	1 day/24°C (75°F) 7 days/24°C (75°F)	-9 -9	-8 -13	0 -6	3.7 4.6
JP-8 Jet Engine Fuel	FVMQ (75 Durometer)	7 days/163°C (325°F) 28 days/163°C (325 F)	-11 -18	0 -73	-8 -38	12 14
Manufactured Gas (24% Methane, 3% Ethane, 18% Carbon Monoxide, 55% Hydrogen)	FVMQ	2 mo/121°C (250°F)	GR	GR	GR	GR

MQ - methyl groups only

V - vinyl groups

P - phenyl groups

F - fluorine-containing groups

GR - good resistance

Fuels (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Gasohol 10%; Methanol/ 90%; No Lead Gasoline	FVMQ	1 day/24°C (75°F) 7 days/24°C (75°F) 14 days/24°C (75°F) 28 days/24°C (75°F)	-19 -19 -20 -21	-47 -19 -48 -50	-35 -26 -26 -26	27.5 25.9 26.6 24.4
Gasohol 10%; Ethanol/90%;	FVMQ	1 day/24°C (75°F) 7 days/24°C (75°F)	-18 -16	-37 -37	-19 -16	21.5 21.3
Unsymmetrical Dimethyl Hydrazine	VMQ FVMQ	4 days/24°C (75°F)	nil DT	-25 DT	-50 DT	60 DT

Hydraulic Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Aerosafe 2300 (Stauffer)	VMQ	70 hr/25°C (77°F)	-12	-26	-17	21
	VMQ FVMQ	70 hr/70°C (158°F)	-15 -49	-36 -97	-5 -62	22 18
Exxon WS2406 Fluid	MQ VMQ PMQ	7 days/71°C(160°F)	-15 -10 -20	-	-	15 20 35
	MQ VMQ PMQ	1 day/121°C (250°F)	-5 -10 -5	-	-	20 35 45
	MQ VMQ PMQ	1 hr/177°C (350°F)	-10 -10 -15	-	-	15 20 30
Hydrolube H-2 Fluid	MQ VMQ PVMQ	70 hr/24°C (75°F)	-5 -5 -5	-15 nil -15	10 15 -10	5 5 5
	MQ PMQ	5 days/24°C (75°F)	-5 -10	-	-	5 10
	MQ PMQ	14 days/24°C (75°F)	-5 -10	-	-	10 15
	MQ PMQ	27 days/24°C (75°F)	-5 -10	-	-	10 15
	MQ PMQ	5 days/65°C (150°F)	-10 -10	-	-	10 20
	MQ PMQ	24 days/65°C (150°F)	-5 -10	-	-	15 20
	MQ VMQ PVMQ	7 days/70°C (158°F)	-10 -10 -5	-10 - -15	20 - -10	5 5 5
Oronite M2V (Chevron)	VMQ FVMQ	7 days/100°C (212°F)	-19 -3	-57 nil	-62 -16	73 2
	VMQ FVMQ	7 days/150°C (302°F)	-24 nil	-70 -22	-63 -12	96 4
	VMQ FVMQ	7 days/177°C (350°F)	-35 -4	-86 -34	-77 -38	130 5

MQ - methyl groups only

V - vinyl groups

P - phenyl groups

F - fluorine-containing groups

DT - deteriorated

Hydraulic Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Oronite 8200 Fluid (Chevron)	FVMQ	3 days/177°C(350°F)	-15	-10	-10	5
Oronite 8515 Fluid (Chevron)	FVMQ	1 day/-54°C (-65°F)	nil	5	5	nil
	MQ VMQ PVMQ	3 days/24°C (75°F)	-15 -20 -15	- - -	- - -	40 45 40
	MQ VMQ PVMQ	3 days/130°C (265°F)	-20 -30 -25	- - -	- - -	60 80 115
	FVMQ	3 days/150°C(302°F) 3 days/177°C (350°F) 3 days/200°C (392°F)	-5 -10 -45	-10 -40 -95	-10 -5 -40	5 10 15
Oronite Hyjet (Chevron)	FVMQ VMQ	70 hr/70°C(158°F)	-25 -10	-79 -4	59 9	24 9
Pydraul 60 Fluid	VMQ PVMQ FVMQ	3 days/24°C (75°F)	-5 -10 -5	- - -	- - -	5 5 5
	VMQ PVMQ FVMQ	3 days/121°C (250°F)	-10 -25 -15	- - -	- - -	10 10 5
Pydraul A-200 Fluid	VMQ PVMQ FVMQ	3 days/24°C (75°F)	-5 -10 -5	- - -	- - -	5 5 nil
	VMQ PVMQ FVMQ	3 days/121°C (250°F)	-10 -10 -5	- - -	- - -	10 15 5
	VMQ PVMQ FVMQ	1 day/177°C (350°F)	-5 -10 -5	- - -	- - -	15 120 5
Pydraul F9 Fluid	MQ VMQ PMQ PVMQ	3 days/24°C (75°F)	-5 -5 -10 -10	-15 - - nil	nil - - 5	5 5 10 5
	MQ VMQ PMQ PVMQ FVMQ	3 days/150°C (302°F)	-5 -5 -10 -10 -5	-15 nil - nil -5	-5 10 - -5 5	10 10 15 15 5
	FVMQ	3 days/177°C (350°F)	-10	-60	-15	-10
Pydraul 150	FVMQ	7 days/150°C (302°F)	DT	DT	DT	DT
Skydrol 500B (Monsanto)	VMQ PVMQ	70 hr/70°C (158°F)	-9 -15	-17 -24	3 -11	10 19
Skydrol HT (Monsanto)	VMQ PVMQ	70 hr/70°C (158°F)	-13 -24	-23 -50	-8 -32	20 40

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Hydraulic Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Skydrol LD (Monsanto)	VMQ FVMQ	70 hr/70°C (158°F)	-16 -37	-22 -87	-3 -71	26 108
Skydrol LD-4 (Monsanto)	FVMQ	1 day/24°C (75°F) 1 day/70°C (158°F)	-24 -29	-82 -85	-68 -73	68 87
Skydrol 7000 Fluid (Monsanto)	MQ VMQ PVMQ	3 days/24°C (75°F)	-5 nil -10	-10 -5 -10	-5 -5 -5	5 5 10
	MQ PMQ	14 days/24°C (75°F)	nil -10	-	-	5 5
	MQ VMQ PVMQ	3 days/93°C (200°F)	-5 -5 -10	-10 -10 -15	nil -10 -10	5 5 10

Transformer and Instrument Oils

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Askerol Transformer Oil (Monsanto) - Chlorinated	VMQ	35 days/24°C (75°F) 44 days/24°C (75°F) 60 days/24°C (75°F) 7 days/70°C (158°F) 14 days/70°C (158°F) 28 days/70°C (158°F) 38 days/70°C (158°F) 1 day/121°C (250°F) 3 days/121°C (250°F) 7 days/121°C (250°F) 14 days/121°C (250°F)	nil -5 -5 -5 -5 -5 -5 -5 -5 -10 -5	-20 -10 -10 -10 -20 -15 -15 -15 -15 -15 -10	-15 -15 -15 -20 -20 -15 -15 -15 -15 -15 -15	10 10 10 10 15 10 15 20 20 15 20
Inerteen Transformer Oil (Westinghouse) - Chlorinated	MQ VMQ PVMQ	3 days/24°C (75°F)	-5 -5 -10	-10 -10 -15	-5 -5 -15	10 10 15
	MQ PVMQ FVMQ	3 days/115°C (240°F)	-10 -10 nil	-25 -25 -15	-5 -10 nil	15 15 5
	VMQ	3 days/177°C (350°F)	-15	-25	-15	30
N-43 Fluorocarbon Capacitor Fluid	VMQ PVMQ	3 days/150°C (302°F)	-5 nil	-	-	5 5
Pyranol Transformer Oil (General Electric) - Chlorinated	PMQ	7 days/100°C (212°F)	-10	-	-	25
RCA-Gulf Instrument Oil A	VMQ PVMQ	3 days/93°C (200°F)	-20 -30	-	-	70 5
Univolt 35 Transformer Oil	MQ VMQ PVMQ FVMQ	3 days/150°C (302°F)	-15 -15 -30 nil	-25 -45 -30 -10	-20 -45 -15 nil	40 50 55 5

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

Transformer and Instrument Oils (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Wemco C Transformer Oil	MQ VMQ PVMQ	3 days/24°C (75°F)	-15 -20 -30	- - -	- - -	35 40 45
	VMQ	1 yr/79°C (175°F)	-35	-	-	40
	VMQ FVMQ	3 days/177°C(350°F)	-55 -5	- -20	- 5	140 10
Coolanol 35 (Monsanto)	VMQ FVMQ	3 days/121°C (250°F)	-21 1	-67 1	-68 -10	101 3
Coolanol 45 (Monsanto)	FVMQ	70 hr/177°C(350°F)	-3	-12	-14	4

Speciality Oils, Greases and Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
ANG 15 Industrial Grease (Texaco Regal Starfak Special)	MQ VMQ	3 days/24°C (75°F)	-5 -10	nil nil	nil nil	10 10
	MQ VMQ	3 days/150°C (302°F)	-10 -15	nil nil	nil nil	20 20
ANG 25 Diester Base (Texaco TG-749)	VMQ	3 days/25°C (77°F)	-5	-	-	15
ANG 25 Diester Base (Texaco TG-749)	PMQ	3 days/93°C (200°F) 1 day/150°C (302°F) 7 days/ 150°C (302°F)	-15 -20 TB	- - TB	- - TB	30 40 TB
ANG 25 Glycerol Ester (Texaco)	PMQ	1 day/71°C (160°F)	-10	-	-	10
ANO No. 3 Grade M; Extreme Pressure (GAF Corp.)	MQ PMQ	3 days/177°C (350°F)	- -	- -	- -	45 30
ANO No. 6 Oil (GAF Corp.)	MQ PMQ	1 day/24°C (75°F)	-10 -10	- -	- -	30 45
	MQ PMQ	7 days/24°C (75°F)	-15 -20	- -	- -	35 60
	MQ PMQ	1 day/150°C (302°F)	-25 -25	- -	- -	95 145
ANO No. 9 Oil (GAF Corp.)	MQ PMQ	1 day/121°C (250°F)	-10 -15	- -	- -	35 40
	MQ PMQ	3 days/121°C (250°F)	-15 -20	- -	- -	45 70
	MQ PMQ	7 days/121°C(250°F)	-15 -20	- -	- -	45 65
ANO No. 11 Oil (GAF Corp.)	MQ PMQ	1 day/121°C (250°F)	-5 -15	- -	- -	10 20
	MQ PMQ	3 days/121°C (250°F)	-10 -15	- -	- -	15 25
	MQ PMQ	7 days/121°C (250°F)	-10 -15	- -	- -	15 25
ANO No. 366 Oil (GAF Corp.)	MQ PMQ	3 days/93°C (200°F)	-20 -10	- -	- -	95 140

MQ - methyl groups only

V - vinyl groups

P - phenyl groups

F - fluorine-containing groups

TB - too brittle to test

Speciality Oils, Greases and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Aroclor 1254 (Monsanto)	VMQ	3 days/24°C (75°F) 3 days/150°C(302°F)	-5 -10	10 -5	5 nil	5 10
Cosmoline 2046 (Fritzsche, Dodge & Olcutt)	VMQ	4 days/24°C (75°F)	-35	-	-	55
Crude Oil 7 API	FVMQ	14 days/24°C (75°F)	-	-	-	5
	VMQ	3 days/83°C (180°F)	-10	-	-	25
	FVMQ	14 days/83°C (180°F) 14 days/135°C (275°F)	- -10	- -	- -	5 5
Crude Oil 315 API	VMQ	14 days/24°C (75°F) 3 days/83°C (180°F)	- -20	- -	- -	10 60
	FVMQ	14 days/83°C (180°F) 14 days/135°C (275°F)	- -5	-70	-45	5 -2
	PVMQ	1 day/100°C (212°F)	-15	-15	15	10
Delco No. 9	VMQ PVMQ	5 days/100°C (212°F)	-10 -15	-	-	10 10
	MQ VMQ	5 days/100°C (212°F)	-5 -5	-	-	5 5
Dowtherm A Heat Transfer Oil (Dow)	VMQ	3 days/24°C (75°F) 3 days/177°C (350°F)	-10 -30	-	-	10 40
FC-75 Fluorochemical Fluid (3M)	VMQ	1 day/24°C (75°F)	-5	-	-	nil
	PVMQ		-5	-	-	nil
	FVMQ		5	-	-	nil
	VMQ	7 days/65°C (150°F)	nil	-	-	5
	PVMQ		-5	-	-	5
	FVMQ		nil	-	-	5
Gas Drip Oil	VMQ PVMQ FVMQ	3 days/24°C (75°F)	-25 -30 -5	-	-	250 500 20
GE Transil Oil	VMQ	3 days/24°C (75°F) 3 days/93°C (200°F)	-20 -30	-	-	35 50
GM 14X Heavy Duty Oil	VMQ	5 days/100°C (212°F)	-5	-	-	5
Mineral Oil	VMQ PVMQ	3 days/24°C (75°F)	-10 -15	-30 -20	-10 -10	25 35
Mineral Oil (Shell No. 5)	VMQ PVMQ	3 days/121°C (250°F)	-20 -35	-55 -55	-35 -20	60 75
	MQ PMQ	1 day/100°C (212°F)	-10 -5	-	-	25 40
	MQ PMQ	1 day/121°C (250°F)	-15 -10	-	-	25 40
	MQ PMQ	1 day/149°C (300°F)	-15 -10	-	-	30 55

MQ - methyl groups only

V - vinyl groups

P - phenyl groups

F - fluorine-containing groups

Speciality Oils, Greases and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Navy Crankcase Oil No. 2135	VMQ	4 days/93°C (200°F)	-15	-	-	10
Navy Crankcase Oil No. 9250	VMQ	4 days/93°C (200°F)	-10	-	-	10
Pacemaker Fluid 100T	VMQ PVMQ	1 day/177°C (350°F)	-25 -35	-	-	50 60
	VMQ PVMQ FVMQ	3 days/177°C (350°F)	-30 -40 -5	- - -20	- - -10	55 65 5
	MQ VMQ PMQ	1 day/71°C (160°F)	-15 -15 -20	- - -	- - -	15 15 30
PRL 3313 (Rohm and Haas)	MQ PMQ	3 days/71°C (160°F)	DT DT	DT DT	DT DT	DT DT
	MQ VMQ PMQ	1 day/121°C (250°F)	DT -25 DT	DT - DT	DT - DT	DT 20 DT
	MQ PMQ	70 hr/24°C (75°F)	-10 -10	-	-	5 10
SG 4766 Glycol Ester Base Grease (Standard Oil)	MQ PMQ	3 days/24°C (75°F)	-10 -10	-	-	10 15
	PMQ	1 day/71°C (160°F) 3 days/71°C (160°F)	-10 -10	-	-	10 10
	FVMQ	70 hr/150°C (302°F) 140 hr/150°C(302°F)	-5 -11	-9 -24	-25 -32	8 10
Shell Aircraft Turbine Lubricant A	FVMQ	70 hr/150°C (302°F) 140 hr/150°C (302°F)	-3 -8	-26 -71	-50 -69	6 7
Shell B & B Grease	VMQ	70 hr/74°C (165°F) 912 hr/74°C (165°F)	-15 -16	-34 -9	-10 -20	26 26
	PMQ	70 hr/74°C (165°F) 912 hr/74°C (165°F)	-17 -19	-11 -15	-7 -13	30 30
Socony Mobil RL 147-A No. 7	PMQ	1 day/150°C (302°F) 6days/150°C (302°F)	-15 -20	-	-	50 50
Sun Oil No. 8X2513-1 L	PMQ	1 day/150°C (302°F) 6days/150°C (302°F)	-25 -45	-	-	70 55
Tectyl 502C Rust Inhibitor	MQ	14 days/24°C (75°F)	-5	5	5	nil
Tectyl 511-M Rust Inhibitor	MQ	14 days/24°C (75°F)	nil	5	-5	nil
Texas 1500 Oil (HD Concentrate)	MQ	10 days/150°C (302°F) 21 days/150°C (302°F)	-15 -20	-20 -30	-20 -10	10 10

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Speciality Oils, Greases and Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Tricresyl Phosphate	MQ VMQ PVMQ	3 days/24°C (75°F)	nil nil nil	nil -5 -5	-5 5 -5	nil nil nil
	MQ VMQ PVMQ	3 days/177°C (350°F)	nil -5 nil	-40 -25 -45	-40 -10 -50	5 5 5
	VMQ	3 days/200°C (392°F)	DT	DT	DT	DT
Turbo Oil No. 35	PVMQ	7 days/24°C (75°F) 7 days/65°C (150°F)	-15 -20	-35 -35	-20 -25	15 15
	VMQ PMQ	3 days/71°C (160°F)	-10 -15	-10 -35	-15 -25	10 15
	VMQ PMQ	3 days/121°C (250°F)	-15 -15	-10 -35	-15 -20	10 15
	FVMQ	3 days/150°C (302°F)	-10	-30	25	10
Ucon Lubricant LB1145 (gear oil) (Union Carbide)	MQ VMQ PMQ	3 days/150°C (302°F)	nil nil nil	- - -	- - -	nil nil nil
Ucon Water-Soluble Lubricant 50-HB-55 (Union Carbide)	MQ VMQ PMQ	3 days/150°C (302°F)	-5 -5 nil	- - -	- - -	nil nil nil
Ucon Lubricant 50-HB-100 (Union Carbide)	MQ VMQ PMQ	3 days/150°C (302°F)	nil -5 nil	- - -	- - -	nil nil nil
Ucon Lubricant 50-HB-260 (Union Carbide)	MQ VMQ PMQ	3 days/150°C (302°F)	nil nil nil	- - -	- - -	nil nil nil
Ucon Lubricant 50-HB-280-X (Union Carbide)	MQ VMQ	3 days/150°C (302°F)	-5 -5	- -	- -	nil nil
Ucon Lubricant 50-HB-660 (Union Carbide)	MQ VMQ PMQ	3 days/150°C (302°F)	nil nil nil	- - -	- - -	nil nil nil
Ucon Lubricant 50-HB-5100 (Union Carbide)	MQ VMQ PMQ	3 days/150°C (302°F)	nil nil nil	- - -	- - -	nil nil nil

Solvents

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Acetone	MQ VMQ PVMQ FVMQ	7 days/24°C (75°F)	-10 -10 -10 -20	- - - -85	- - - -75	25 15 20 180
Benzene	VMQ FVMQ	14 days/24°C (75°F)	-	- -22	- -15	175 23
	FVMQ	3 days/70°C (158°F)	-10	-50	-40	20

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Solvents (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Butyl Acetate	VMQ PMQ PVMQ	7 days/24°C (75°F)	-30 nil -25	- - -	- - -	150 150 125
Butyl Alcohol (Butanol)	MQ VMQ PMQ PVMQ FVMQ	7 days/24°C (75°F)	-10 -10 -15 -10 nil	- - - - -	- - - - -	20 15 40 35 10
Carbon Tetrachloride	VMQ PVMQ FVMQ	7 days/24°C (75°F)	-20 -10 -5	- - -45	- - -30	165 165 20
	FVMQ	5 days/49°C (120°F)	-10	-	-	20
Chlorobromomethane	FVMQ	7 days/24°C (75°F)	-10	-45	-50	25
	MQ VMQ PVMQ	2 days/67°C(153°F)	-20 -20 -25	- - -	- - -	70 95 235
Chloroform	FVMQ	5 days/24°C (75°F)	-10	nil	nil	30
Chlorothene Solvent (Dow)	FVMQ	1 day/24°C (75°F)	-15	-	-	50
	VMQ	7 days/24°C (75°F)	-	-	-	245
Cyclohexane	FVMQ	2 days/24°C (75°F)	-	-	-	15
	VMQ	7 days/24°C (75°F)	-	-	-	250
Diacetone Alcohol	VMQ	5 days/24°C (75°F)	-5	-	-	5
Dichloroisopropyl Ether	PMQ	7 days/24°C (75°F)	-	-	-	nil
Diethyl Ether	FVMQ	7 days/24°C (75°F)	-10	-40	-45	50
Ethyl Alcohol	MQ VMQ PVMQ FVMQ	7 days/24°C (75°F)	-5 -5 -10 nil	- - - -30	- - - -15	nil 5 20 5
Ethylenedichloride	FVMQ	3 days/24°C (75°F)	-10	-	-	50
	VMQ	7 days/24°C (75°F)	-	-	-	45
Heptane	FVMQ	7 days/60°C (140°F)	-10	-30	-30	25
Isopropyl Alcohol	PMQ	7 days/24°C (75°F)	-10	-	-	10
Methyl Alcohol	MQ	7 days/24°C (75°F)	nil	nil	nil	nil
Methyl Chloride	FVMQ	14 days/25°C (77°F)	-12	-34	-11	4
	MQ VMQ PVMQ	7 days/24°C (75°F)	NR -15 -15	NR - -	NR - -	NR 150 150
Methylene Chloride	VMQ FVMQ	72 hr/25°C (77°F)	- -	- -	- -	180 70
Mineral Spirits	FVMQ	30 days/24°C (75°F)	nil	nil	nil	nil
Monochlorobenzene	FVMQ	7 days/24°C (75°F)	-5	-45	-40	25

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

NR - not recommended

Solvents (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Naphtha	FVMQ	3 days/24°C (75°F)	-	-	-	10
Nitrocellulose Solvent (Toluene, Ethyl Alcohol, Ethyl Acetate, Methyl Ethyl Ketone, Butyl Acetate)	VMQ PVMQ FVMQ	2 days/24°C (75°F)	-25 -45 -25	- - -	- - -	135 165 65
Ortho-Chloroethylbenzene	FVMQ	7 days/24°C (75°F)	-5	-55	-40	15
Ortho-Chlorotoluene	FVMQ	7 days/24°C (75°F)	-5	-45	-45	20
Oxylene Solvent	FVMQ	1 day/24°C (75°F)	-15	-	-	90
Perchloroethylene	FVMQ	3 days/24°C (75°F)	-10	-	-	10
	PMQ	14 days/24°C (75°F)	-10	-	-	45
	FVMQ	1 day/107°C (225°F)	-15	-	-	20
Propylenedichloride	FVMQ	5 days/49°C (120°F)	-10	-	-	55
Solvatone Solvent (Union Carbide)	VMQ	1 day/24°C (75°F)	-15	-	-	30
Stoddard Solvent	MQ VMQ PVMQ	7 days/24°C (75°F)	NR -20 -15	NR - -	NR - -	NR 160 150
Toluene	MQ VMQ PVMQ FVMQ	7 days/24°C (75°F)	NR - -20 -10	NR - -50	NR - -35	NR 205 150 20
Toluene Vapor	PMQ	14 days/24°C (75°F)	-10	-	-	50
Turpentine	VMQ FVMQ	16 hr/24°C (75°F)	- -	- -	- -	230 15
Xylene (Xylol)	VMQ	15 min/24°C (75°F) 30 min/24°C (75°F) 1 hr/24°C (75°F) 2 hr/24°C (75°F) 5 days/24°C (75°F)	-20 -25 -30 -30 -35	- - - - -	- - - - -	40 45 60 80 135
	FVMQ	3 days/24°C (75°F) 7 days/24°C (75°F)	-10 -10	-45 -55	-35 -40	20 20

Silicone Fluids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
XIAMETER® PMX-200 Silicone Fluid, 0.65 centistokes	FVMQ	3 days/24°C (75°F) 1 day/100°C (212°F) 3 days/150°C (302°F)	-5 -5 -10	-45 - -60	-30 - -30	5 15 25
XIAMETER® PMX-200 Silicone Fluid, 3 centistokes	FVMQ	3 days/24°C (75°F) 3 days/150°C (302°F)	nil -10	-15 -30	-10 -10	nil 10
XIAMETER® PMX-200 Silicone Fluid, 10 centistokes	FVMQ (40 Durometer)	3 days/23°C (73°F) 14 days/23°C (73°F) 3 days/100°C (212°F) 14 days/100°C (212°F)	-1 -2 -3 -1	-5 -9 -4 -6	3 0 3 0	0 0 1 1
XIAMETER® PMX-200 Silicone Fluid, 100 centistokes	FVMQ (40 Durometer)	3 days/23°C (73°F) 14 days/23°C (73°F) 3 days/100°C (212°F) 14 days/100°C (212°F)	-3 -4 -4 -3	3 1 6 5	7 5 10 10	0 0 0 0

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

NR - not recommended

Silicone Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Change	Hardness Change points	Tensile Change %	Elongation Change %	Volume %
XIAMETER® PMX-200 Silicone Fluid, 1000 centistokes	FVMQ (40 Durometer)	3 days/23°C (73°F) 14 days /23°C (73°F) 3 days/100°C (212°F) 14 days/100°C (212°F)	-3 -4 -5 -2	3 1 -2 0	4 2 0 5	0 0 1 0
XIAMETER® PMX-200 Silicone Fluid, 60000 centistokes	VMQ PMQ FVMQ	1 day 24°C (75°F)	-5 -5 nil	-10 -10 -10	nil -10 nil	5 5 nil
	PMQ FVMQ	3 days/24°C (75°F)	-5 nil	-15 -10	-5 -15	5 nil
	VMQ PMQ FVMQ	7 days/24°C (75°F)	-5 -10 nil	-10 -5 -5	nil -5 nil	10 10 nil
	VMQ PMQ FVMQ	1 day 150°C (302°F)	-5 -10 -5	-15 -5 -15	-10 nil -5	15 10 nil
	VMQ PMQ FVMQ	3 days/150°C (302°F)	-10 -10 -5	-15 -15 -25	-10 -10 nil	15 10 nil
	VMQ PMQ FVMQ	7 days/150°C (302°F)	-10 -10 -5	-30 nil -25	-20 -25 -15	15 15 nil
Dow Corning® 210 Fluid (other side of rubber exposed to air)	FVMQ	2 mo/121°C (250°F)	NE	NE	NE	NE
Dow Corning® 210 H Fluid, 1000 centistokes	FVMQ	16 hr/260°C (500°F)	-	-	-	-3
Dow Corning® 210 H Fluid, 6000 centistokes	75/25 VMQ/FVMQ 50/50 VMQ/FVMQ	70 hr/177°C (350°F) 70 hr/177°C (350° F)	-10 -10	-16 -13	-20 -21	11 8
Dow Corning® 220 Fluid	FVMQ	2 days/150°C (302°F)	nil	-	-	10
Dow Corning® 510 Fluid	MQ VMQ PVMQ	3 days/24°C (75°F)	-15 -15 -20	-	-	40 35 35
	VMQ	1 day/150°C (302°F)	-20	-	-	35
	MQ VMQ PVMQ FVMQ	3 days/150°C (302°F)	-20 -25 -30 nil	-	-	40 45 50 nil
	MQ VMQ PVMQ	3 days/24°C (75°F)	-5 -5 -10	-	-	5 10 10
Dow Corning® 550 Fluid	MQ VMQ PVMQ	3 days/150°C (302°F)	-10 -10 -10 nil	-	-	10 10 10 nil
	VMQ	7 days/150°C (302°F)	-	-	-	10

MQ - methyl groups only

V - vinyl groups

P - phenyl groups

F - fluorine-containing groups

NE - no effect

Silicone Fluids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Dow Corning® 702 Fluid	VMQ	1 day/150°C (302°F)	-25	-	-	60
Dow Corning® 703 Fluid	VMQ	1 day/150°C (302°F)	-25	-	-	50
Dow Corning® 710 Fluid	FVMQ	3 days/150°C (302°F)	nil	nil	-15	nil
	VMQ	7 days/150°C (302°F) 7 days/150°C (302°F) 7 days/200°C (392°F)	-5 -10 -10	- - -	- - -	5 5 10
Dow Corning® 710 Fluid	MQ VMQ PVMQ	3 days/24°C (75°F)	-5 -5 -5	- - -	- - -	nil 5 5
	MQ VMQ PVMQ	3 days/150°C (302°F)	-10 -5 -10	- - -	- - -	5 5 10
	FVMQ	14 days/200°C (392°F)	-20	-70	10	nil
Dow Corning® FS-1265 Fluid	VMQ FVMQ PVMQ	7 days/150°C (302°F)	nil -20 -5	10 -55 15	-5 -45 -10	nil 80 5

Silicone Compounds and Greases

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Dow Corning® 4 Compound	PMQ	1 day/24°C (75°F) 3 days/24°C (75°F) 7 days/24°C (75°F)	-5 -5 -5	- - -	- - -	5 10 20
	MQ VMQ PMQ	1 day/150°C (302°F)	-20 -15 -5	- - -	- - -	25 25 15
	VMQ PMQ	3 days/150°C (302°F)	- -10	- -	- -	25 25
	VMQ PMQ	7 days/150°C (302°F)	- -10	- -	- -	30 30
	PMQ	1 day/200°C (392°F) 3 days/200°C (392°F) 7 days/200°C (392°F)	-10 -20 -30	- - -	- - -	20 30 40
Dow Corning® 5 Compound	MQ VMQ	1 day/150°C (302°F)	-20 -15	- -	- -	20 15
Dow Corning® 11 Compound	PMQ	1 day/150°C (302°F) 3 days/150°C (302°F) 1 day/200°C (392°F) 1 day/250°C (482°F)	nil nil nil -25	- - - -	- - - -	10 10 10 nil
Dow Corning® 33 Grease	FVMQ	3 days/25°C (77°F) 3 days/177°C (350°F)	-5 -11	- -	- -	4 9

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

Silicone Compounds and Greases (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Dow Corning® 44L Grease	VMQ	7 days 150°C (302°F)	-	-	-	15
Dow Corning® 55 Pneumatic Grease	PMQ	3 days/93 °C (200 °F) 3 days /250°C (482°F)	-15 DT	- DT	- DT	60 DT
	VMQ FVMQ	3 days/177°C (350°F) 3 days/25°C (77°F) 3 days/177°C (350°F)	DT -5 -11	DT - -	DT - -	DT 4 9
Dow Corning® Heat Sink Compound 304	VMQ	70 hr/150°C (302°F)	-9			11
Dow Corning® FS-1281 Compound	VMQ FVMQ	7 days/70°C (158° F)	-5 -10	-	-	5 10
Dow Corning® FS-1292 Grease	75/25 VMQ/FVMQ 50/50 VMQ/FVMQ	70 hr/177°C(350°F) 70 hr/177°C (350°F)	-6 -17	-11 1	-28 -6	6 16

Food Products

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Beer	VMQ FVMQ	22 hr/70°C (158°F)	nil -5	-	-	nil nil
Butter (liquid)	VMQ FVMQ	22 hr/70°C(158°F)	-5 -3	- -	- -	nil nil
Coca-Cola Syrup	VMQ PVMQ FVMQ	1 day/24°C (75°F)	nil nil 5	nil 10 nil	nil 15 5	nil nil nil
	VMQ PVMQ FVMQ	28 days/24°C (75°F)	nil nil nil	-10 20 nil	-10 20 10	nil nil nil
	VMQ PVMQ FVMQ	60 days/24°C (75°F)	nil nil 5	-10 -5 -5	-10 -5 -5	nil nil nil
Coffee	VMQ	7 days/83°C(180°F) 14 days/83°C (180° F)	-5 -5	-15 -5	nil nil	nil 5
Lard	VMQ (High Strength)	1 day/200°C (392°F) 3 days/200°C (392°F) 7 days/200°C (392°F)	nil -5 BR	-35 -80 BR	-40 -75 BR	5 5 BR
	VMQ	7 days/200°C (392°F) 1 hr/260°C (500°F)	nil -10	-30 -25	-35 -20	nil 5
Mazola Oil	VMQ	7 days/150°C (302°F)	-5	-15	-10	nil
Orange Peel Oil	VMQ	1 day/24°C (75°F)	-	-	-	-100

MQ - methyl groups only

V - vinyl groups

P - phenyl groups

F - fluorine-containing groups

DT - deteriorated

BR - brittle

Food Products (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Orange Syrup	VMQ PVMQ FVMQ	1 day/24°C (75°F)	nil nil nil	nil 5 -15	5 10 5	nil nil 5
	VMQ PVMQ FVMQ	28 days/24°C (75°F)	nil nil -5	-5 15 -15	-5 25 5	nil nil nil
	VMQ PVMQ FVMQ	60 days/24°C (75°F)	nil nil -5	-5 nil -35	-10 5 -15	nil nil 5
Scotch Whisky	VMQ PVMQ FVMQ	1 day/24°C (75°F)	nil nil nil	nil nil -15	-5 5 3	nil nil 5
	VMQ PVMQ FVMQ	28 days/24°C (75°F)	nil nil -5	-5 5 -15	10 20 15	nil nil nil
	VMQ PVMQ FVMQ	60 days/24°C (75°F)	nil nil -5	-10 -10 -35	5 -5 -15	nil 5 3
Spry Shortening	VMQ	7 days/150°C (302°F)	-5	-15	-15	nil
Tab Concentrate	VMQ PVMQ FVMQ	1 day/24°C (75°F)	nil nil nil	nil nil -5	5 3 3	nil nil nil
	VMQ PVMQ FVMQ	28 days/24°C (75°F)	nil nil nil	5 5 nil	30 10 10	nil nil nil
	VMQ PVMQ FVMQ	60 days/24°C (75°F)	nil nil nil	nil -5 -10	-10 -5 -5	nil nil nil
Tia Maria Liquor	VMQ PVMQ FVMQ	1 day/24°C (75°F)	nil nil nil	nil 10 -10	5 10 3	nil nil nil
	VMQ PVMQ FVMQ	28 days/24°C (75°F)	nil nil -5	nil 10 -15	10 10 20	nil nil nil
	VMQ PVMQ FVMQ	60 days/24°C (75°F)	nil nil -5	-5 -5 -25	-5 nil -5	nil nil nil
Vegetable Oil (Kraft)	VMQ (High Strength)	1 day/200°C (392°F) 3 days/200°C (392°F) 7 days/200°C (392°F)	-5 nil -5	-30 -40 -80	-25 -45 -75	5 5 5
Vinegar	VMQ (High Strength)	1 day/24°C (75°F) 7 days/24°C (75°F)	nil nil	-5 -5	nil nil	nil nil

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

Water and Steam

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Water	MQ VMQ PVMQ	7 days/24°C (75°F)	nil nil nil	-5 - -5	-5 - -10	5 nil nil
	MQ VMQ PVMQ	7 days/70°C (158°F)	-5 nil -5	-5 -5 -10	5 10 -5	5 nil nil
	VMQ PVMQ FVMQ	3 days/100°C (212°F)	-5 -3 nil	-5 -5 -	-15 -5 -	nil nil nil
	MQ VMQ	7 days/100°C (212°F)	-5 nil	-20 -	20 -	nil 5
	VMQ	14 days/100°C (212°F)	nil	-	-	5
	MQ	1 day/121°C (250°F) 3 days/121°C (250°F)	-5 -5	- -	- -	5 5
	FVMQ	70 hr/150°C (302°F)	-5	-	-	nil
	MQ	1 day/177°C (350°F) 3 days/177°C (350°F)	-15 DT	- DT	- DT	15 DT
Steam	MQ VMQ PVMQ	7 days/5 psi	-5 -5 -5	-25 -15 -10	5 5 10	nil 5 nil
	MQ VMQ PVMQ	14 days/5 psi	-5 -5 -5	-35 -30 -3	-10 -15 10	5 3 nil
	MQ VMQ PVMQ	7 days/10 psi	-5 -5 -5	-30 -30 -10	-10 -10 -10	5 5 nil
	MQ VMQ PVMQ	14 days/10 psi	-5 -5 -5	-35 -40 -10	-15 -20 -10	5 5 nil
	MQ VMQ PVMQ	7 days/20 psi	-5 -5 -3	-35 -35 -15	-15 -20 -15	5 3 nil
	MQ VMQ PVMQ	14 days/20 psi	-5 -5 -5	-45 -45 -20	-20 -40 -15	5 5 nil
	VMQ	1 day/50 psi 3 days/50 psi 5 days/50 psi 7 days/50 psi	-5 -5 -5 -5	-25 -30 -40 -65	-10 -5 -25 -30	5 5 5 5

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Water and Steam (cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Steam	VMQ	1 day/65 psi 3 days/65 psi 7 days/65 psi 1 day/80 psi 3 days/80 psi 7 days/80 psi	-10 -5 -10 -10 -10 -10	-30 -50 -65 -40 -60 -75	-30 -25 -50 -10 -40 -45	5 5 5 5 10 5
	MQ	16 hr/100psi	-10	-30	25	nil
	MQ VMQ* PVMQ FVMQ	1 day/100 psi	-10 3 -5 -5	-40 -11 -25 -20	-10 -2 5 15	5 -2 nil nil
	MQ VMQ PVMQ	3 days/100 psi	-10 4 -10	-60 -25 -35	-20 -10 -5	10 -4 nil
	MQ VMQ PVMQ	7 days/100 psi	-20 6 -20	-30 -35 -75	-25 -26 -75	5 -6 nil

Acids

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Acetic Acid (5%)	VMQ	7 days/24°C (75°F)	-5	-	-	5
Acetic Acid, glacial	MQ VMQ PVMQ	7 days/24°C (75°F)	-5 -5 -5	- - -	- - -	nil 5 5
	FVMQ	2 days/24°C (75°F)	-	-	-	20
	VMQ FVMQ	1 day/100°C (212°F)	-30 -15	- -	- -	100 10
Hydrochloric Acid (5% in Perchloroethylene)	MQ VMQ PVMQ FVMQ	7 days/24°C (75°F)	nil -5 nil -5	- - - -25	- - - -15	nil nil nil nil
Hydrochloric Acid (10%)	FVMQ	3 days/24°C (75°F) 3 days/65°C (150°F)	nil nil	-20 -35	-10 -10	nil 10
Hydrochloric Acid (36%, concentrated)	MQ VMQ PVMQ FVMQ	7 days/24°C (75°F)	PR -5 BR -5	PR - BR -45	PR - BR -30	PR 5 BR 10
Hydrofluoric Acid (48%)	PMQ	9 days/27°C (80°F)	DT	DT	DT	DT
Nitric Acid (10%)	MQ VMQ PVMQ FVMQ	7 days/24°C (75°F)	nil nil nil nil	- - - -10	- - - -3	10 nil nil nil

* Data based on *Silastic*® NCP-80 and NCP-40 Silicone Rubber.

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
PR - poor

BR - brittle

Acids (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Nitric Acid (50%)	FVMQ	3 days/24°C (75°F) 3 days/65°C (150°F)	5 -10	-15 -80	-10 -30	5 5
Nitric Acid (70%, concentrated)	MQ VMQ PVMQ FVMQ	7 days/24°C (75°F)	PR 5 BR nil	PR - BR -40	PR - BR -30	PR -10 BR 5
Phosphoric Acid (10%)	MQ PMQ	7 days/24°C (75°F)	UA UA	UA UA	UA UA	UA UA
	MQ PMQ	7 days/100°C (212°F)	UA UA	UA UA	UA UA	UA UA
Phosphoric Acid (85%, concentrated)	MQ PMQ	7 days/24°C (75°F)	UA UA	UA UA	UA UA	UA UA
	VMQ FMQ	7 days/100°C (212°F)	UA 4	-39 -8	nil -9	-23 -2
Stearic Acid	MQ PMQ	7 days/100°C (212°F)	UA UA	UA UA	UA UA	UA UA
Sulfuric Acid (20%)	MQ	1 day/83°C (180°F) 7 days/83°C (180°F)	nil nil	-10 -25	-5 -15	-5 -10
Sulfuric Acid (30%)	PVMQ	2 hr/93°C (200°F)	nil	-20	-5	nil
Sulfuric Acid (50%)	FVMQ	3 days/24°C (75°F) 3 days/65°C (150°F)	nil 5	-5 -35	-5 -15	nil nil
Sulfuric Acid (95%. concentrated)	MQ VMQ FVMQ PVMQ	7 days/24°C (75°F)	DC DC DC DC	DC DC DC DC	DC DC DC DC	DC DC DC DC

Bases

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Ammonium Hydroxide (saturated)	MQ VMQ PMQ PVMQ FVMQ	7 days/24°C (75°F)	-5 nil UA nil -5	- - UA - -45	- - UA - -5	nil nil UA 0 5
Calcium Oxide (10%, saturated)	VMQ	1 day/150°C (302°F)	5	-15	-10	5
Lithium Hydroxide (2%)	VMQ	1 day/150°C (302°F)	nil	-25	-10	-5
Lithium Hydroxide (5%)	VMQ	1 day/150°C (302°F)	-10	-70	nil	-35
Lithium Hydroxide (10%, saturated)	VMQ	1 day/150°C (302°F)	DT	DT	DT	DT
Potassium Hydroxide (10%)	VMQ	1 day/150°C (302°F)	5	-20	-15	-5
Potassium Hydroxide (25%)	MQ PMQ	7 days/83°C (180°F)	nil -5	- -	- -	5 nil
Potassium Hydroxide (saturated)	VMQ	1 day/150°C (302°F)	-20	-40	-10	-10

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
BR - brittle

PR - poor
UA - unaffected
DC - decomposed

Bases (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Sodium Hydroxide (10%)	MQ VMQ PMQ PVMQ FVMQ	7 days/24°C (75°F)	-5 -5 - -5 -5	- - - - -45	- - - - -10	nil nil 5 nil nil
Sodium Hydroxide (25%)	MQ PMQ	7 days/83°C (180°F)	-5 -5	- -	- -	nil -10
Sodium Hydroxide (50%)	VMQ PMQ FVMQ	7 days/24°C (75°F)	-5 - -5	- - -10	- - 5	nil 10 nil
	PMQ	7 days/100°C (212°F)	-	-	-	15

Salts

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Copper Sulfate (50%)	PMQ	5 days/100°C (212°F)	UA	UA	UA	UA
Ferric Chloride (60%)	MQ PMQ	7 days/100°C (212°F)	UA FR	UA FR	UA FR	UA FR
Sodium Carbonate (2%)	MQ VMQ PVMQ	7 days/24°C (75°F)	nil -5 5	- - -	- - -	nil nil nil
Sodium Chloride (10%)	MQ VMQ PVMQ	7 days/24°C (75°F)	nil nil 5	- - -	- - -	nil nil nil

Other Chemicals

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Acetonitrile	VMQ FVMQ	20 hr/24°C(75°F)	- -	- -	- -	nil 5
	VMQ FVMQ	168hr/150°C (302°F)	- DI	- DI	- DI	5 DI
Ammonia	MQ VMQ PVMQ	7 days/24°C (75°F)	nil -10 -5	- - -	- - -	nil nil 5
	VMQ FVMQ	24hr/110°C(230°F) 300 lb. pressure	- DT	260 DT	200 DT	- DT
Aniline	FVMQ	7 days/24°C (75°F)	nil	-30	-15	5
Bromine (liquid)	MQ	7 days/24°C (75°F)	25	-	-	15
Butylene Oxide	MQ PMQ	1 day/24°C (75°F)	- -	- -	- -	20 40
Calcium Silicate (10%. saturated)	VMQ	1 day/150°C (302°F)	nil	nil	nil	5
Caprolactam Monomer	VMQ FVMQ	3 days/24°C (75°F)	nil -5	-20 -20	-10 nil	nil nil

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
UA - unaffected

FR - fair
DI - disintegrated

Other Chemicals (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
1-Chlorodecane	FVMQ	7 days/24°C (75°F)	-5	-20	-20	10
Dimethyl Formamide	FVMQ	1 day 24°C (75°F)	DT	DT	DT	DT
	MQ PMQ	7 days/24°C (75°F)	nil nil	- -	- -	2 2
Dioctyl Phthalate	VMQ	3 days/70°C (158°F) 6 days/70°C (158°F) 70 hr/150°C (302°F)	-1 -5 -15	-10 -16 -4	-12 -9 8	10 11 13
	FVMQ	70 hr/150°C (302°F)	-9	-13	-13	7
Dowtherm 209 (Dow) (50/50 Water)	VMQ	14 days/100°C (212°F)	2	-7	-17	nil
Ethylene Glycol	FVMQ	7 days/24°C (75°F)	nil	-10	-10	nil
Ethylene Glycol (60%)	MQ	7 days/135°C (275°F)	-25	-	-	20
Ethylene Glycol (50%)	VMQ FVMQ	7 days/83°C (180°F)	nil nil	nil -5	10 5	nil nil
	VMQ	70 hr/100°C (212°F) 7 days/100°C (212°F) 14 days/100°C (212°F)	-1 -7 -4	-4 -5 -10	nil 2 -12	1 nil 1
	PVMQ	7 days/121 °C (250°F)	-5	-	-	5
Ethylene Glycol Mixture ($\frac{1}{3}$ Ethylene Glycol; $\frac{1}{3}$ Ethyl Alcohol; $\frac{1}{3}$ Water)	VMQ	7 days/100°C (212°F)	-1	-2	2	5
Ethylene Oxide	MQ	3 days/24°C (75°F)	-	-	-	25
	FVMQ	7 days/24°C (75°F)	-15	-75	-60	100
	VMQ	7 days/71°C (160°F)	-30	-70	-65	95
	MQ	14 days/71°C (160°F)	-	-	-	45
	PVMQ	32hr/110°C (230°F)	nil	-25	-30	nil
Freon 11 (DuPont)	VMQ PVMQ FVMQ	3 days/24°C (75°F)	- - -	- - -	- - -	175 260 30
Freon 12 (DuPont)	VMQ PVMQ FVMQ	3 days/24°C (75°F)	- - -	- - -	- - -	150 195 45
Freon 21 (DuPont)	MQ	7 days/-55°C (-67°F) 7 days/24°C (75°F)	-5 -15	- -	- -	225 165
Freon 22 (DuPont)	MQ FVMQ MQ VMQ	7 days/-55°C (-67°F) 3 days/24°C (75°F) 7 days/24°C (75°F)	-10 - -5 -5	- - - -	- - - -	110 205 75 75

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated

Other Chemicals (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Freon 113 (DuPont)	MQ	7 days/-55°C (-67°F) 7 days/24°C (75°F)	-5 -5	- -	- -	200 150
Freon 114 (DuPont)	VMQ PVMQ FVMQ	3 days/24°C (75°F)	- - -	- - -	- - -	130 135 25
HMS 20-1083	VMQ PVMQ	3 days/24°C (75°F)	-20 -15	- -	- -	125 100
Hydrazine (Anhydrous)	FVMQ	3 days/24°C (75°F)	ES	ES	ES	ES
Hydrogen Peroxide (3%)	PMQ	7 days/24°C (75°F)	UA	UA	UA	UA
Hydrogen Peroxide (30%)	PMQ	7 days/24°C (75°F)	UA	UA	UA	UA
Hydrogen Peroxide HTP (90%)	FVMQ	7 days/65°C (150°F)	nil	-20	-15	5
Isopropyl Nitrate	FVMQ	7 days/24°C (75°F)	-	-	-	200
Methyl Methacrylate	VMQ FVMQ	4 hr/25°C (77°F)	- -	- -	- -	106 104
Molybdenum Disulfide	VMQ PVMQ FVMQ	3 days/24°C (75°F)	nil nil nil	- - -	- - -	nil nil nil
	VMQ PVMQ FVMQ	3 days/150°C (302°F)	nil nil 5	- - -	- - -	nil nil nil
Monoethanolamine	VMQ	70 hr/24°C (75°F) 70 hr/38°C (100°F)	nil -5	-20 -25	5 5	nil 5
	VMQ FVMQ	70 hr/121°C (250°F)	-25 DT	-80 DT	-5 DT	5 DT
Pentachlorophenol (10% in Ethanol)	PMQ	7 days/24°C (75°F)	-	-	-	5
Phenol (70%)	MQ	7 days/100°C (212°F)	-30	-	-	5
Phenol (85%)	MQ	7 days/24°C (75°F)	-10	-	-	10
Phthalic Acid Anhydride	MQ	7 days/149°C (300°F)	5	-	-	nil
Phthalic Anhydride	MQ VMQ FVMQ	1 day/200°C (392°F)	nil nil nil	- - -	- - -	nil nil nil
	MQ VMQ FVMQ	5 days/200°C (392°F)	-2 nil -2	- - -	- - -	nil nil 7
	MQ VMQ FVMQ	7 days 200°C (392°F)	-2 nil 2	- - -	- - -	2 nil 7

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
UA - unaffected

ES - excessive swell

Other Chemicals (Cont.)

Immersion Medium	ASTM Designation	Immersion Conditions	Hardness Change points	Tensile Change %	Elongation Change %	Volume Change %
Polyglycol (Dow 80-6)	VMQ PVMQ	7 days/24°C (75°F)	-5 -5	- -	- -	5 5
	MQ VMQ	7 days/ 121°C (250°F)	-5 -10	- -	- -	5 5
Polystyrene (expandable)	VMQ	7 days/24°C (75°F)	nil	5	10	nil
Propylene Oxide	MQ	7 days/24°C (75°F)	-20	-	-	150
RX-1099 (Vinyl Plastisol)	VMQ FVMQ	7 days/24°C (75°F)	-5 -5	- -	- -	10 5
Salicylanilide (10% in 2 B Ethanol)	PMQ	7 days/24°C (75°F)	-	-	-	5
Santicizer 141 (Monsanto)	VMQ PVMQ FVMQ	70 hr/150°C (302°F)	DT DT DT	DT DT DT	DT DT DT	DT DT DT
Styrene Monomer	PVMQ	1 hr/24°C (75°F) 1 hr/100°C (212°F)	-10 -20	- -	- -	55 115
Sulfur (molten)	PMQ	7 days/121°C (250°F)	UC	UC	UC	UC
	VMQ	4 days/199°C (390°F)	-22	DT	DT	DT
Sulfur Dioxide (dry gas)	MQ VMQ PVMQ	7 days/24°C (75°F)	nil -5 nil	- - -	- - -	nil nil nil
Sulfur Dioxide (liquid)	MQ	7 days/24°C (75°F)	nil	-	-	5
Sulfur Hexafluoride	VMQ FVMQ	1 day/150°C (302°F)	nil nil	- -	- -	nil nil
	VMQ FVMQ	2 days/199°C (390°F)	nil 5	- -	- -	nil nil
	VMQ FVMQ	3 days/199°C (390°F)	nil 5	- -	- -	nil nil
	PMQ	7 days/100°C (212°F)	nil	-	-	10
Tetrahydrofuran (Tetramethylene Oxide)	VMQ FVMQ	1 day/25°C (77°F)	- -	- -	- -	260 170
Trichloroethylene	FVMQ	1 day/24°C (75°F)	-10	-	-	25
	MQ	7 days/24°C (75°F)	-	-	-	250
	FVMQ	5 days/49°C (120°F)	-10	-	-	20
Trifluorochloroethylene	MQ	7 days/-58°C (-65 °F)	-20	-	-	100

MQ - methyl groups only
V - vinyl groups

P - phenyl groups
F - fluorine-containing groups

DT - deteriorated
UC - unchanged

For information about silicone elastomers from Dow Corning

A global leader in silicones, silicon-based technology and innovation, Dow Corning offers an extensive line of silicone elastomers that meet performance requirements across a wide range of industrial and consumer applications.

Silastic brand silicone elastomers are ideal for customers who require specialty materials, collaborative problem-solving support or exact solutions to complex challenges. For product and service information, visit dowcorning.com/rubber.

XIAMETER brand silicone rubber products are designed for customers who simply need an efficient way to buy reliable, high-quality standard materials at market-driven prices. For product information, visit xiometer.com.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Dow Corning is a registered trademark of Dow Corning Corporation.

We help you invent the future is a trademark of Dow Corning Corporation.

XIAMETER is a registered trademark of Dow Corning Corporation.

Silastic is a registered trademark of Dow Corning Corporation.

©2000, 2006, 2009 Dow Corning Corporation. All rights reserved.

Printed in USA

AGP9790

Form No. 45-0113E-01

DOW CORNING

We help you invent the future.TM

